

This page is mainly introduced the SA-564 S15700 chemical information, mechanical properties, physical properties, mechanical properties, heat treatment, and Micro structure, etc. It also contains the use of SA-564 S15700, such as it is commonly used in bars, sheet, plates, steel coils, steel pipes, forged and other materials application.

Data Table for Grades Stainless Steels SA-564 S15700

SA-564 S15700 Standard Number:			
ITEM Standard Number Descriptions		Descriptions	
1	SA-564/SA-564M	Hot-Rolled and Cold-Finished Age-Hardening Stainless Steel Bars and Shapes	

SA-564 S15700 Chemical composition(mass fraction)(wt.%)				
Chemical	Min.(%)	Max.(%)		
С		0.09		
Mn		1.00		
Si		1.00		
Р		0.04		
S		0.03		
Cr	14.00	16.00		
Ni	6.50	7.75		
Мо	2.00	3.00		
Al	0.75	1.50		

SA-564 S15700 Physical Properties			
Tensile strength	115-234	σb/MPa	
Yield Strength	23	σ 0.2 ≥/MPa	
Elongation	65	δ5≥ (%)	
Ψ	-	ψ≥ (%)	
Akv	-	Akv≥/J	
HBS	123-321	-	
HRC	30	-	





SA-564 S15700 Chemical information, Mechanical properties

Physical properties, Mechanical properties, Heat treatment, and Micro structure

Tensile strength	231-231	σb/MPa
Yield Strength	154	σ 0.2 ≥/MPa
Elongation	56	δ5≥(%)
Ψ	-	ψ≥(%)
Akv	-	Akv≥/J
HBS	235-268	-
HRC	30	-

SA-564 S15700 Heat Treatment Regime				
Annealing	Quenching	Tempering	Normalizing	Q & T
V	√	√	V	√

SA-564 S15700 Range of products				
Product type	Products	Dimension	Processes	Deliver Status
Plates / Sheets	Plates / Sheets	0.08-200mm(T)*W*L	Forging, hot rolling and cold rolling	Annealed, Solution and Aging, Q+T, ACID- WASHED, Shot Blasting
Steel Bar	Round Bar, Flat Bar, Square Bar	Φ8-1200mm*L	Forging, hot rolling and cold rolling, Cast	Black, Rough Turning, Shot Blasting,
Coil / Strip	Steel Coil /Steel Strip	0.03-16.0x1200mm	Cold-Rolled & Hot- Rolled	Annealed, Solution and Aging, Q+T, ACID- WASHED, Shot Blasting
Pipes / Tubes	Seamless Pipes/Tubes, Welded Pipes/Tubes	OD:6-219mm x WT:0.5-20.0mm	Hot extrusion, Cold Drawn, Welded	Annealed, Solution and Aging, Q+T, ACID- WASHED

We can produce Stainless Steels the specifications follows:

Note:

(1) listed in the table apex diameter (d), to steel thickness (a) multiples said.

(2) in the ASTM A6 standard specified scope can meet any additional conditions.

(3) from the standard for 50 mm (2 in).

Mechanical properties

Mechanische Eigenschaften

Caracteristiques mecaniques

ReH Minimum yield strength / Mindestwert der oberen Streckgrenze / Limite d'elasticite minimale

Rm Tensile strength / Zugfestigkeit / Resistance a la traction

A Minimum elongation / Mindestwert der Bruchdehnung / Allongement minimal

J Notch impact test / Kerbschlagbiegeversuch / Essai de flexion par choc

Round bar:

Diameter: 1mm-2000mm

Square bar:



SA-564 S15700 Chemical information, Mechanical propertie

Physical properties, Mechanical properties, Heat treatment, and Micro structure

Size: 50mm * 50mm-600mm *600mm

Plate steel/flat bar:

Size: Thickness: 0.1mm-800mm Width: 10mm to 1500mm

Tube/pipe:

Size: OD: 6-219mm WT: 1-35 mm.

Cold-rolled sheet: Thickness: 2-5mm Width:1000mm Length: 2000mm

Hot-rolled sheet: Thickness:6-80mm Width: 210-610mm

Length: We can supply any length based on the customer's requirement.

Forging/hot rolling/ extrusion of steel.

Forging: Shafts with flanks/pipes/tubes/slugs/donuts/cubes/other shapes

Finished goods condition: hot forging/hot rolling + annealing/normalizing + tempering/quenching + tempering/any

conditions based on the customer's requirement

Surface conditions: scaled (hot working finish)/ground/rough machining/fine machining/based on the customer's requirement

Furnaces for metallurgical processing: electrode arc + LF/VD/VOD/ESR/Vacuum consumable electrode.

Ultrasonic inspection: 100% ultrasonic inspection for any inperfections or based on the customer's requirement.

UTS according to SEP 1921 C/c,D/d,E/e;A388 or GB/T 6402

Excellent service for all kinds of industries, with advantages of technologies, equipment and price.

We serve you with our honesty, integrity, and professionality.

Email: sales@tool-die-steels.com http://www.tool-die-steels.com/ Page 3 / 3