

This page is mainly introduced the X19CrMoVNbN11-1 chemical information, mechanical properties, physical properties, mechanical properties, heat treatment, and Micro structure, etc. It also contains the use of X19CrMoVNbN11-1, such as it is commonly used in bars, sheet, plates, steel coils, steel pipes, forged and other materials application.

Data Table for Grades Stainless Steels X19CrMoVNbN11-1

X19CrMoVNbN11-1 Standard Number:

ITEM	Standard Number	Descriptions
1	DIN 17240 (1976)	Heat Resisting and Highly Heat Resisting Materials for Bolts and Nuts; Quality Specifications

X19CrMoVNbN11-1 Chemical composition(mass fraction)(wt.%)

Chemical	Min.(%)	Max.(%)
C	0.16	0.22
Si	0.10	0.50
Mn	0.30	0.80
P		0.035
S		0.035
Cr	10.0	11.5
Mo	0.50	1.00
Ni	0.30	0.80
V	0.10	0.30
Nb	0.15	0.50
N	0.05	0.19

X19CrMoVNbN11-1 Physical Properties

Tensile strength	115-234	σ_b /MPa
Yield Strength	23	$\sigma_{0.2} \geq$ /MPa
Elongation	65	$\delta 5 \geq$ (%)
ψ	-	$\psi \geq$ (%)
Akv	-	$Akv \geq$ /J
HBS	123-321	-
HRC	30	-

X19CrMoVNbN11-1 Mechanical Properties

Tensile strength	231-231	σ_b /MPa
Yield Strength	154	$\sigma_{0.2} \geq$ /MPa
Elongation	56	$\delta_5 \geq$ (%)
ψ	-	$\psi \geq$ (%)
Akv	-	Akv \geq /J
HBS	235-268	-
HRC	30	-

X19CrMoVNbN11-1 Heat Treatment Regime

Annealing	Quenching	Tempering	Normalizing	Q & T
√	√	√	√	√

X19CrMoVNbN11-1 Range of products

Product type	Products	Dimension	Processes	Deliver Status
Plates / Sheets	Plates / Sheets	0.08-200mm(T)*W*L	Forging, hot rolling and cold rolling	Annealed, Solution and Aging, Q+T, ACID-WASHED, Shot Blasting
Steel Bar	Round Bar, Flat Bar, Square Bar	Φ8-1200mm*L	Forging, hot rolling and cold rolling, Cast	Black, Rough Turning, Shot Blasting,
Coil / Strip	Steel Coil /Steel Strip	0.03-16.0x1200mm	Cold-Rolled & Hot-Rolled	Annealed, Solution and Aging, Q+T, ACID-WASHED, Shot Blasting
Pipes / Tubes	Seamless Pipes/Tubes, Welded Pipes/Tubes	OD:6-219mm x WT:0.5-20.0mm	Hot extrusion, Cold Drawn, Welded	Annealed, Solution and Aging, Q+T, ACID-WASHED

We can produce Stainless Steels the specifications follows: